



PARQUET SEALANT FLEXI WOOD FILLER

Date:01/06/07

Page 1 of 3

Product Description :

Flexi wood filler is high quality, plasto-elastic, one-component , wood coloured joining material

Characteristics :

- Paintable with varnish
- Ready to sand after 24 hours
- Water-resistant
- No scent
- Non-aggressive

Applications :

- Joints with movements up to 15 %
- Filling of joints and openings between parquet

Application Examples :

- Joints between walls and different types of parquet or laminate flooring
- Joints between floors and skirting boards
- Joints between wooden floors and walls
- Around laminated flooring edges and build in cupboard joints
- For the sealing of joints on cupboards, wardrobes, kitchen cupboards, cooking tops and other wooden items

Packaging and Colours :

Colours : White, Oak, Cherry, Beech, Teak, Maple, Birch, Pine, Meranti
Packaging : Cartridges of 300 ml

Shelflife :

Store in a cool, dry storage place at temperatures between +5°C and +25°C.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.



PARQUET SEALANT FLEXI WOOD FILLER

Date:01/06/07

Page 2 of 3

Technical Data :

Base :	Co-polymer Dispersion
Consistency :	Stable Paste
Curing System :	Physical Drying
Skin Forming :	The surface is dry after 20 min
Hardening Time :	Does not apply
Shrinkage :	Approx. 15%
Specific Gravity :	Approx. 1.6g/ml
Temperature Resistance :	-20°C to + 80°C
Maximum deformation :	15 %

Surfaces :

Substrate :	All types of parquet and laminate parquet. All porous building substrates.
State of Surface :	Dry, clean, dust- and greasefree
Preparation :	Prepare very porous surfaces with thinned Parquet Sealant (1 part Parquet Sealant and 2 parts water)

Joint Size :

Minimum :	5 mm
Maximum :	20 mm
Minimum Depth :	5 mm
Recommandation :	Depth of Joint = Width of Joint

Application :

Application Method :	Manual or Pneumactical Caulking Gun. Apply into joint and smoothen with a humid cloth. Remove excess material before drying. The joint can be sandpapered after full cure.
Application Temperature:	+5°C to +30°C, do not apply when rain or frost are imminent
Clean with :	Water immediatly after application
Repair with :	Global Parquet Sealant

Transport Information :

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.



PARQUET SEALANT FLEXI WOOD FILLER

Date:01/06/07

Page 3 of 3

Road :	ADR :	Free
Maritime :	IMDG :	Free
Air :	ICAO/IATA-DGR :	Free
UN Number :		Free

Labelling :

Symbol :	None
R-Sentences :	None
S-Sentences :	None

Safety Measures :

Apply the usual work hygienics

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.